

Nox-Crete Silcoseal Select




New generation, chemically active cure and bondbreaker for tilt-up, lift slab and precast construction. Complies with ASTM C-309 curing requirements.

How-it-works






SILCOSEAL SELECT is a new generation cure and tilt-up bondbreaker. In contrast to most conventional cure and bondbreakers, SILCOSEAL SELECT does not contain any wax or hydrocarbon resins and, as a result, does not depend on a physical barrier deposited on top of the casting slab to prevent bonding.





Instead, SILCOSEAL SELECT consists of a special formulation of chemically reactive organic compounds in a predominately water based solvent system which chemically react with calcium hydroxide, a byproduct of the cement hydration reaction, present in the concrete surface pores. The reaction products are amorphous gels which, in conjunction with other combined special organic compounds in SILCOSEAL SELECT, effectively seal concrete surface pores. Moisture entry or exit is restricted, allowing good retention of concrete mixing water to assist in providing proper cement hydration and concrete curing, minimizing concrete surface cracking and crazing. Properly applied, SILCOSEAL SELECT positively prevents the bonding of tilt wall panels to casting slab floor surfaces.

Applications




-  Use as a cure & bondbreaker in tilt-up & precast concrete construction.
-  Use to cure the top side of tilt wall panels to prevent the formation of shrinkage cracks.
-  Use as a cure only on all types of interior, smooth troweled concrete where the use of conventional resin based curing compounds is impractical.

Advantages








-  Provides improved resistance to the “osmotic effect” by restricting the natural tendency for water to migrate from freshly placed panel concrete through the bondbreaker film and into the less moist casting slab. Reducing the “osmotic effect” greatly improves panel concrete surface appearing resulting in a smooth, uniform, surface profile, colour and appearance.
-  Achieves exceptional wall panel surface appearance.
-  Leaves no residue or resulting staining on wall panel or casting slab floor surfaces when properly applied.
-  Achieves a crisp, positive release that minimizes panel surface defect and reduces panel resurfacing/patching costs.
-  Excellent resistance to washoff from normal rain showers and dew when applied directly to previously uncoated concrete surfaces

-  Does not contain any wax or hydrocarbon resins like many conventional bondbreakers which often leave a difficult-to-remove residue on wall panel and casting slab surfaces. When this residue is not properly removed, it often causes floor and exterior wall panel paint and coating adhesion problems.
-  Dust, dirt and mud can be easily removed from casting slab floor surfaces by washing with low pressure water when SILCOSEAL SELECT is used as both the cure and bondbreaker.
-  Resistant to sunlight induced oxidation damage that can necessitate the reapplication of competitive bondbreakers even when panel concrete placement is delayed a few days.
-  Green Engineered™ – better for health and the environment.

Precautions

-  Not recommended for use as a bondbreaker on broom-finished or rough-finished concrete surfaces.
-  Not recommended for application over any other manufacturer’s inorganic silicate based floor sealer, hardener or organic resin based curing, sealing or combination cure and seal product. Failure to follow this recommendation can result in panel surface defects or panel sticking.
-  Carefully inspect all casting slab surfaces prior to concrete placement to ensure and adequate film of bondbreaker is uniformly applied.

Nox-Crete Silcoseal Select

-  If a delay of more than 2 weeks occurs between the final bondbreaker application coat and panel concrete placement, it will be necessary to check for a sufficient bondbreaker film on the casting slab. If the bondbreaker film is sufficient, the bondbreaker must be reapplied as necessary before concrete placement.
-  Not recommended for application over or in conjunction with any other manufacturer's tilt-up bondbreaker.
-  Not recommended for application in the rain or if rain is anticipated within 6 hours of application. Surfaces exposed to rain or running water within this time period will require reapplication.
-  Not recommended for bondbreaker application to casting slab surfaces previously cured with polyethylene or curing blankets without first removing all salt deposits. Failure to remove all salt deposits can result in panel surface blemishes or defects.
-  Not recommended for application to frozen casting slab surfaces or when ambient temperatures are below 4°C or expected to drop below 4°C within 12 hours following application.
-  Not recommended for application without the proper spray equipment. See USE INSTRUCTIONS for specific sprayer and tip size recommendations.
-  Not recommended for cure coat application prior to saw cutting crack control joints. Best results are obtained when SILCOSEAL SELECT cure coat is applied immediately after final finishing and joint saw cutting has been completed.

Use Instructions

- Request current product literature, labels and material safety data sheets from manufacturer and read thoroughly before product use.
- Site environmental conditions, substrate conditions and construction have a major effect on product selection, application methods, procedures and rates, appearance and performance. Product literature provides general information applicable to some conditions. However, an adequate site test application by the purchaser or installer in advance of field scale use is mandatory (irrespective of any other verbal or written representations) to verify that product and quantities purchased can be satisfactorily applied and will achieve desired appearance and performance under intended use conditions.
- Use the NOX-CRETE DRUM AGITATOR to adequately mix product before withdrawing from the container and before each use.
- Apply using REID TOTAL SPRAY APPLICATOR. The recommended spray tip size is 8001 or 8004. Coarser (8005-LP) spray tips should be used on porous casting slab surfaces

where additional bondbreaker is necessary to ensure sufficient film holdout. The use of an improper sprayer and/or incorrect spray tip generally results in either over or under application.

- SILCOSEAL SELECT should be applied in accordance with recommended procedures to achieve even and uniform coverage. Equipment should be clean and dry prior to use.
- Typical drying time is 30 minutes to 3 hours, but varies with the presence or absence of a moisture barrier beneath the casting slab, climatic conditions and application rate. Extended drying times in excess of 24 hours are possible in cure coat applications when product is applied heavily during cool weather and a moisture barrier is present. Reducing the application rate and applying in multiple thin coats in lieu of one heavy coat will greatly reduce drying time.
- Avoid scouring the casting slab surface during panel concrete placement by using a deflection board.

Cure Coat Application

- Apply to the point of rejection and uniform surface film accumulation immediately after final finishing and joint saw cutting.
- The typical application range is 5-10 m2/litre but can vary widely depending upon the specific conditions such as concrete mix design, type of finish and ambient weather conditions. For example, concrete floors which are cast during cool and humid conditions require less SILCOSEAL SELECT to achieve optimum curing than do concrete floors cast during hot, dry and windy conditions.
- Over application can result in delays due to slow drying. Under application can result in shrinkage cracking or crazing and excessively porous and weakened slab surfaces.

IT IS THE CONTRACTOR'S RESPONSIBILITY TO EVALUATE THE CONDITIONS ON EACH PROJECT AND TO DETERMINE THE CORRECT APPLICATION RATE OF THE SILCOSEAL CURE COAT. IF UNSURE, CONTACT REID FOR SPECIFIC RECOMMENDATIONS

Bond Breaker Application

- Casting slab areas should be well cured, smooth and dense.
- Remove all dust, dirt, saw cut residue, standing water and other contaminants prior to applying bondbreaker coats.
- The number of bondbreaker coats and related application rate required to achieve complete, uniform coverage of casting slab varies with concrete mix design, placing and finishing procedures, weather conditions, etc. Because of this, it is not possible to prescribe application rates or procedures inclusive of all site variables.
- Best results are obtained when successive coats of SILCOSEAL SELECT are applied at right angles (perpendicular) to each other.

Nox-Crete Silcoseal Select

- Typical coverage rates are 15 - 17 m²/lt for the first coat, and 20 - 25 m²/lt for subsequent coats.
- An adequate application is indicated by the presence of a dry soap-like feel uniformly apparent to touch over the entire treated area with no indication of greater accumulations in low spots or depressions. Following bondbreaker application and immediately prior to panel concrete placement, be certain casting slab surfaces evidence the dry soap-like feel, but do not evidence over application of SILCOSEAL SELECT as indicated by a slippery or grease-like feel to the touch. Over application may result in retardation of panel skin or dusting, surface irregularities and/or discolouration as well as unreacted bondbreaker residue on panel and floor surfaces.
- Typically, casting slab surfaces which are more porous resulting from such conditions as improper curing, the addition of pozzolans such as fly ash or which received a more open or less tight finish will require more SILCOSEAL SELECT than slab surfaces which are less porous.
- Rain occurring prior to product drying will necessitate reapplication of bondbreaker.
- Do not apply to reinforcing steel or lifting inserts.
- Avoid spray drifts, runs or puddles. Promptly wipe up any material excesses which can lead to subsequent adhesive failure of floor coatings and wall paints.

IT IS THE CONTRACTOR'S RESPONSIBILITY TO EVALUATE THE CONDITIONS ON EACH PROJECT AND TO DETERMINE THE CORRECT APPLICATION RATE OF THE SILCOSEAL BONDBREAKER COATS. IF UNSURE, CONTACT REID FOR SPECIFIC RECOMMENDATIONS

! CAUTION: THE PRIMARY REASON FOR PANELS STICKING TO CASTING SLABS IS AN INADEQUATE FILM OF BONDBREAKER ON THE CASTING SLAB SURFACE AT THE TIME OF PANEL CONCRETE PLACEMENT. IT IS YOUR RESPONSIBILITY TO VERIFY A CONTINUOUS FILM OF BONDBREAKER CAN BE FELT ON THE CASTING SLAB SURFACE AS PREVIOUSLY DESCRIBED IMMEDIATELY PRIOR TO PLACEMENT OF PANEL CONCRETE.

Casting Slabs Cured With SILCOSEAL SELECT

- Apply successive coats of SILCOSEAL SELECT until the casting slab surface appears uniformly dark in appearance for at least 2-3 hours following the last coat. If the treated slab appears light in colour either generally or in spots within 2-3 hours of last application, excessive slab porosity is indicated. Reapply SILCOSEAL SELECT to all light-coloured areas. If areas of light colour or dry appearance persist, thoroughly wet affected areas with water to fill concrete surface pores, squeegee off excess water and immediately re-apply SILCOSEAL SELECT.

- The application rate can vary widely depending upon the specific conditions. Do not over or under apply.

Existing Casting Slabs

- Verify concrete surface is free of substances that could adversely affect product performance
- If a curing or sealing compound was used, it will be necessary to remove the coating from the casting slab surface prior to applying bondbreaker.
- Apply successive coats of SILCOSEAL SELECT until the casting slab surface appears uniformly dark in appearance for at least 2-3 hours following the last coat. If the treated slab appears light in colour either generally or in spots within 2-3 hours of last application, excessive slab porosity is indicated. Reapply SILCOSEAL SELECT to all light-coloured areas. If areas of light colour or dry appearance persist, thoroughly wet affected areas with water to fill concrete surface pores, squeegee off excess water and then immediately re-apply SILCOSEAL SELECT.
- The typical effective coverage rate for all combined bondbreaker coats applied to existing, clean and unsealed casting slabs is 9-11m²/litre. The application rate can vary widely depending upon the specific conditions. Do not over or under apply.

Cleaning

To clean panel surfaces, pretreat the areas to be cleaned with a detergent solution consisting of 225 grams of trisodium phosphate in 3.8 litres of water. Rinse the detergent solution off with water using a minimum 4,000 psi power washer.

Determine adequacy of the surface preparation of panels and casting slabs with appropriate site test to verify acceptable adhesion, appearance and performance of paints, coatings, adhesives, sealers, sealants, grouts, etc prior to application. See ACI515 for specific recommendations.

Technical Data

Colour	Light Blue Liquid
Clarity	Opaque Emulsion
Bulk Density	968.5 grams/litre
Actual Volatile Organic Compound (VOC) Content	<120 grams/litre*
US Regulatory VOC Content	<600 grams/litre
Viscosity	3 cps @ 25°C
Vapour Pressure	<2.13 kPa @ 20°C
Flash Point, ASTM D-92	>78°C

* Complies with VOC requirements for low Solids Coatings

Nox-Crete Silcoseal Select

Handling/Storage

Read Material Safety Data Sheet (MSDS) prior to using. Product is a combustible liquid. Store product at temperatures above 0°C and below 38°C. Following each liquid removal, tightly reseal all container bungs or caps to include mixer port cap that seals opening for drum agitator handle promptly to prevent loss of necessary volatile solvents

! CAUTION: FAILURE TO PROPERLY STORE PRODUCT CAN RENDER IT UNSUITABLE FOR USE

Shelf Life

9 months from date of manufacture. Use product before expiration date indicated on container

Limited Warranty

CONDITIONS OF SALE

- NOX-CRETE offers this product sale subject to, and Buyer and all users are deemed to have accepted, the following conditions of sale and limited warranty which may only be varied by written agreement of a duly authorized corporate officer of NOX-CRETE. No other representative of or for NOX-CRETE is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

- NOX-Crete makes NO OTHER WARRANTY, either express or implied, concerning this product. There is NO WARRANTY OF MERCHANTABILITY. In no case shall NOX-CRETE be liable for special, indirect or consequential damages resulting from the use or handling of the product and no claim of any kind shall be greater in amount than the purchase price of the product in respect of which damages are claimed.

INHERENT RISKS

- NOX-CRETE makes no warranty with respect to the performance of the product after it is applied by the purchaser and the purchaser assumes all risks associated with the use or application of the product.



Packaging & Product Codes

Part No.	Size	Pack
NOXSILCOSEL20	20L	Pail
NOXSILCOSEL200	200L	Drum

Availability and Technical Services

For stockists or technical information, please contact Reid on:
(AU) 1300-780-250
(NZ) 0800 88 22 12